



Физико-механични параметри

ПОЛИУРЕТАН (ПОЛИЕТЕРИЧНИ) ПЯНИ HR TYPE

Комфортни полиуретанови пяни

ТИП		ПЛЪТНОСТ [KG/M³]	ТВЪРДОСТ ILD [N] 40%	ТВЪРДОСТ CLD [kPa] 40%	ЕЛАСТИЧНОСТ MIN. [%]	ДЕФОРМАЦИЯ MAX. [%]	СЪДЪРЖАНИЕ НА ВОДА MAX. [%]	ЯКОСТ НА ОПЪН MIN. [kPa]	ОТНОСИТЕЛНО УДЪЛЖАВАНЕ MIN. [%]
N	kPa								
HR-23040I*	HR-2310I*	21,85-25,30	32,8-47,2	0,82-1,18	45	8	1	60	110
HR-25065	HR-2516	22,50-25,50	45,0-85,0	1,10-2,10	45	7	1	70	100
HR-25065I*	HR-2516I*	23,75-27,50	53,3-76,7	1,33-1,92	45	7	1	70	110
HR-30050	HR-3013	27,50-30,50	35,0-70,0	0,90-1,80	50	10	1	80	110
HR-30050I*	HR-3012I*	28,50-33,00	41,0-59,0	1,02-1,48	50	6	1	80	110
HR-30110	HR-3027	27,50-30,50	90,0-130,0	2,30-3,30	50	6	1	80	110
HR-30110I*	HR-3027I*	28,50-33,00	90,2-129,8	2,25-3,19	50	6	1	80	110
HR-30150	HR-3037	27,50-30,50	130,0-170,0	3,25-4,25	50	6	1	80	110
HR-35120	HR-3530	32,50-35,50	96,0-144,0	2,40-3,60	55	6	1	80	110
HR-35120I*	HR-3530I*	33,25-38,50	98,4-141,6	2,46-3,48	52	6	1	80	100
HR-35160	HR-3540	32,50-35,50	140,0-180,0	3,50-4,50	50	5	1	90	100
HR-40150	HR-4037	37,50-40,50	130,0-170,0	3,30-4,30	55	6	1	100	100
HR-40150I*	HR-4037I*	38,00-44,00	123,0-177,0	3,07-4,42	55	5	1	80	100
HR-50250	HR-5062	47,50-55,00	210,0-290,0	5,25-7,25	55	8	1	90	90
ECO HR 23	ECO HR 23	21,50-24,50	50,0-90,0	1,25-2,25	47	6	1	80	100